

Application No.: 10/806,556  
Docket No.: EL0508USNA

Page 2

**Amendments to Claims**

1. (Original) A conductive composition consisting essentially of
  - (a) 50-95 wt % finely divided particles of an electrically-conductive material dispersed in
  - (b) a liquid vehicle, for use in the manufacture of an electrically-conductive pattern on a substrate for the use of reducing cross-sectional area and width while retaining conductivity and resistivity.
2. (Original) A conductive composition comprising:
  - (a) finely divided particles of an electrically-conductive material;
  - (b) an inorganic binder selected from lead borates, lead silicates, lead borosilicates, cadmium borate, lead cadmium borosilicates, zinc borosilicates, sodium cadmium borosilicates, bismuth silicates, bismuth borosilicates, bismuth lead silicates, bismuth lead borosilicates, oxides or oxide precursors of metals, and mixtures thereof; dispersed in
  - (c) a liquid vehicle wherein the total composition contains 50-95 % by weight solids and wherein said inorganic binder is present at less than 1.0% of the total solids in the composition.
3. (Currently Amended) The composition of ~~any one of Claims 1 or 2~~ wherein said electrically-conductive material is selected from silver, gold, platinum, or palladium and mixtures thereof.
4. (Withdrawn) A process for the manufacture of an electrically-conductive pattern, said process comprising:
  - providing a substrate;
  - providing on at least a part of said substrate a layer of enamel;
  - applying onto said enamel the conductive composition of any one of claims 1 to 3;
  - firing the coated substrate.
5. (Withdrawn) An article comprising a substrate having on at least a part thereof a layer of enamel, and on at least a part of said enamel an electrically-conductive pattern, said electrically-conductive pattern is formed from a conductive composition comprising: (a) finely divided particles of an electrically-conductive material; (b) an inorganic binder selected

Application No.: 10/806,556  
Docket No.: EL0508USNA

Page 3

from lead borates, lead silicates, lead borosilicates, cadmium borate, lead cadmium borosilicates, zinc borosilicates, sodium cadmium borosilicates, bismuth silicates, bismuth borosilicates, bismuth lead silicates, bismuth lead borosilicates, oxides or oxide precursors of metals, and mixtures thereof; dispersed in (c) a liquid vehicle wherein said inorganic binder is present from 0 to 1.0% of the total solids in the composition.

**Please add the following new claims:**

6. (New) The composition of Claim 1 wherein said electrically-conductive material is selected from silver, gold, platinum, or palladium and mixtures thereof.
7. (New) A conductive composition consisting essentially of:  
50-95 wt % finely divided particles of an electrically-conductive material selected from the group consisting of silver, gold, platinum, palladium and mixtures thereof dispersed in a liquid vehicle, selected from an organic vehicle and an aqueous vehicle for use in the manufacture of an electrically-conductive pattern on a substrate for the use of reducing cross-sectional area and width while retaining conductivity and resistivity.
8. (New) The composition of Claim 7 wherein the electrically-conductive material is silver.
9. (New) The composition of Claim 1 wherein the electrically-conductive material is silver.
10. (New) A conductive composition consisting essentially of:  
(a) 50-95 wt % finely divided particles of an electrically-conductive material dispersed in (b) a liquid vehicle, for use in the manufacture of an electrically-conductive pattern on a substrate for the use of reducing cross-sectional area and width while retaining conductivity and resistivity, and wherein the composition does not contain an inorganic binder.

Application No.: 10/806,556  
Docket No.: EL0508USNA

Page 4

11. (New) A conductive composition comprising:
  - (a) finely-divided particles of an electrically-conductive material;
  - (b) an inorganic binder selected from lead borates, lead silicates, lead borosilicates, cadmium borate, lead cadmium borosilicates, zinc borosilicates, sodium cadmium borosilicates, bismuth silicates, bismuth borosilicates, bismuth lead silicates, bismuth lead borosilicates, oxides or oxide precursors of metals, and mixtures thereof; dispersed in (c) a liquid vehicle wherein the total composition contains 50-95 % by weight solids and wherein said inorganic binder is present at less than 0.5% of the total solids in the composition.
12. (New) The composition of claim 2, wherein said inorganic binder is a lead-free inorganic binder.
13. (New) The composition of claim 2, wherein said inorganic binder consists essentially of  $\text{Bi}_2\text{O}_3$ ,  $\text{B}_2\text{O}_3$ ,  $\text{SiO}_2$ ,  $\text{CaO}$ ,  $\text{ZnO}$ , and  $\text{Al}_2\text{O}_3$ .